



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B01L 3/00, C12Q 1/68</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/02266</b> <b>(43) International Publication Date:</b> 21 January 1999 (21.01.99)
<b>(21) International Application Number:</b> PCT/EP98/04938 <b>(22) International Filing Date:</b> 7 July 1998 (07.07.98)  <b>(30) Priority Data:</b> 97202140.6      11 July 1997 (11.07.97)      EP  <b>(71) Applicant (for all designated States except US):</b> AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> VAN DAMME, Hendrik, Sibolt [NL/NL]; Bethaniestraat 9, NL-5211 LG 's-Hertogenbosch (NL). KREUWEL, Hermanus, Johannes, Maria [NL/NL]; Vivaldistraat 10, NL-5481 LW Schijndel (NL).  <b>(74) Agent:</b> KRAAK, H.; P.O. Box 20, NL-5340 BH Oss (NL).		<b>(81) Designated States:</b> AU, CA, ID, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.          Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> A DEVICE FOR PERFORMING AN ASSAY, A METHOD FOR MANUFACTURING SAID DEVICE, AND USE OF A MEMBRANE IN THE MANUFACTURE OF SAID DEVICE		
<b>(57) Abstract</b> <p>The present invention relates to a device for performing an assay, which device comprises a substrate having oriented through-going channels, said channels opening out on a surface for sample application, the channels in at least one area of the surface for sample application being provided with a first binding substance capable of binding to an analyte. The object of the present invention is to provide a substrate having both a high channel density and a high porosity, allowing high density arrays comprising different first binding substances to be applied to the surface for sample application. More in particular, the object of the present invention is to provide a device comprising a relatively cheap substrate that does not require the use of any typical microfabrication technology and, that offers an improved control over the liquid distribution over the surface of the substrate. The above objects are achieved with a device as mentioned above wherein the porous substrate is an electrochemically manufactured metal oxide membrane.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A device for performing an assay, a method for manufacturing said device, and use of a membrane in the manufacture of said device

The present invention relates to a device for performing an assay, which  
5 device comprises a substrate having oriented through-going channels, said channels opening out on a surface for sample application, the channels in at least one area of the surface for sample application being provided with a first binding substance capable of binding to an analyte.

Such a device is disclosed in WO95/11755 for "sequencing by  
10 hybridisation" applications. The device comprises a substrate provided with channels, the channels being oriented substantially perpendicular to the surface of the substrate. Three types of substrate are disclosed. The first type is comprised of a multitude of hollow glass fibres. It is manufactured by stacking glass fibres having an etchable core, providing the stack with flat ends, polishing  
15 those ends, and etching the cores, usually with acid. The second type of substrate is produced by electrochemical etching of a crystalline silicon wafer. First, the position of the channels as well as their size are defined using standard photolithographic methods. Subsequently the oriented channels are formed electrochemically. The third type of substrate is produced by nuclear  
20 track etching of an inorganic substrate. This method, comprising the steps of exposing the substrate to heavy, energetic charged particles and wet-etching, results in a substrate with channels scattered randomly over the surface of the substrate. With higher pore densities and porosity there is more chance of fusion of channels, which show reduced flow resistance with respect to other,  
25 non-fused channels.

All three types of substrates are quite expensive because of the labour-intensive manufacturing processes and/or expensive starting materials and wasteful operations, such as sawing and polishing, and/or expensive equipment. In addition, the substrates are characterised by a relatively low  
30 porosity of 30% and more. More advantageous, higher porosities of up to 80% are said to be achievable, but only at relatively low channel densities, with the disadvantage that the effective surface area of the channels of a particular area

of the substrate is lower in comparison with a substrate having a comparable porosity but with higher channel densities (and consequently narrower channels). A further disadvantage of the silicon-based substrates as disclosed in WO 95/11755 is that they are not transparent for light. These substrates  
5 therefore prohibit the advantageous use of optical marker systems for the detection of analyte bound in the substrate. Popular optical marker systems are for instance based on enzymatically induced colour reactions, on bio- or chemiluminescence, or on photoluminescence. In the latter case both the excitation light and emitted luminescent light have to pass through the substrate material.

10 The object of the present invention is to overcome the above disadvantages and provide a substrate having both a high channel density and a high porosity, allowing even higher density arrays comprising different first binding substances per unit of the surface for sample application. In addition, the substrate is highly transparent for visible light. More in particular, the object  
15 of the present invention is to provide a device comprising a relatively cheap substrate that does not require the use of any typical microfabrication technology and, that offers an improved control over the liquid distribution over the surface of the substrate.

The above objects are achieved with a device wherein the porous  
20 substrate is an electrochemically manufactured metal oxide membrane.

Metal oxide membranes having through-going, oriented channels can be manufactured cheaply through electrochemical etching of a metal sheet. Metals considered are, among others, tantalum, titanium, and aluminium, as well as alloys of two or more metals and doped metals and alloys. The metal oxide  
25 membranes are transparent, especially if wet, which allows for assays using various optical techniques. Such membranes have oriented channels with well controlled diameter and advantageous chemical surface properties.

The invention thus provides a device for performing an assay, which device comprises a substrate having oriented through-going channels, said  
30 channels opening out on a surface for sample application, the channels in at least one area of the surface for sample application being provided with a first

binding substance capable of binding to an analyte, wherein the substrate is an electrochemically manufactured metal oxide membrane.

According to a preferred embodiment, the first binding substance is chosen from the group consisting of a nucleic acid probe, an antibody, an antigen, a  
5 receptor, a hapten, and a ligand for a receptor.

Assays in which the device according to the present invention can be used may include sequencing by hybridisation, immunoassays, receptor/ligand assays and the like.

When the device is used as a tool to obtain DNA sequence information, a  
10 large array of areas is provided, each area comprising as a first binding substance an oligonucleotide probe of a different base-pair sequence. If a sample containing DNA or RNA fragments with a (partly) unknown sequence is brought into contact with the substrate a specific hybridisation pattern may occur, from which pattern the sequence information of the DNA/RNA can be  
15 derived. Such "sequencing by hybridisation" methods are well known in the art (see e.g. Fodor, S.P.A. et al. (1992), Science 251, 767-773 and Southern, E.M. et al. (1994) Nucleic Acids Res. 22, 1368-1373).

The device according to the present invention may also be used to screen a biological specimen, such as blood, for a large number of analytes. The array  
20 may consist of areas comprising oligonucleotide probes specific for, for example, E. coli, S. aureus, S. pneumoniae etc. A biological sample can be prepared as described in EP 0.389.063. If this sample is brought into contact with the substrate, the resulting hybridisation pattern can be read e.g. using a CCD camera in combination with an appropriate optical marker.

25 Apart from screening for bacteria, the device is suitable for the detection of viruses, as well as the classification of different subtypes of, for example, HIV- and HCV viruses, etc. Virus classification may be essential to determine potential drug resistance. In general it requires the ability to detect single point mutations in the virus RNA.

30 The device is also suited for performing sandwich immunoassays. In that case, it is preferred that a second antibody is used for binding to bound analyte, said

second antibody for each of the analyte being recognised by a third labelled antibody. This may be achieved if the second and third antibodies are derived from different species and the third antibody is raised against antibodies of the other species. Thus it is avoided to label the second antibody for each particular analyte.

The device is also suited for performing "pepsans" as disclosed in Geysen et al., Proc. Natl. Acad. Sci. USA 81:3998-4002 (1984). In that case the first binding substances that are attached to the different areas of the substrate constitute different sequences of aminoacids. If the substrate is brought into contact with a liquid that contains a particular analyte, a reaction pattern may occur representing the specific affinity of the analyte for the different aminoacid sequences.

It is preferred that the first binding substance is covalently bound to the substrate.

This minimises loss of the first binding substance from the substrate. Covalent binding of an organic compound to a metal oxide is well known in the art, for example using the method described by Chu, C.W., et al. (J. Adhesion Sci. Technol., 7, pp.417-433, 1993) and Fadda, M.B. et al. (Biotechnology and Applied Biochemistry, 16, pp. 221-227, 1992).

According to a preferred embodiment the metal oxide membrane is comprised of aluminium oxide.

Such a membrane of aluminium oxide appears to have through-going channels that are hydrophilic in comparison to the surface of the membrane. Thus, advantageously, a hydrophilic liquid preferably enters the channels instead of spreading over the surface of the membrane. Therefore aluminium oxide membranes may accommodate for high densities of areas comprising different first binding substances. Aluminium oxide membranes having oriented through-going channels are disclosed by Rigby, W.R. et al. (Trans. Inst. Metal Finish., 68(3), p. 95, 1990) and are marketed by Anotec Separations Ltd., Oxon, UK. These membranes have been used to purify viruses, and to store enzymes

for sensor purposes, but there is no suggestion with respect to their suitability as substrates for performing probe-based assays.

The present invention also relates to a method of manufacturing a device comprising membranes having oriented through-going channels according to the invention, wherein the first binding substance is synthesised in situ.

For example, using only a limited number of reagents, for a device comprising an oligonucleotide as the first binding substance usually four nucleotide compounds (dA, dT, dC, and dG for DNA, A, U, C, and G for RNA) and additional reagents such as blocking reagents, and protecting reagents, classical solid phase synthesis techniques can be used to provide a substrate with one or an array of a plurality of areas with oligonucleotide probes.

Reagents can conveniently be applied to the through-going channels of a particular area using ink-jet technology. Ink-jet technology allows for the accurate deposition of defined volumes of liquid. In situ synthesis of oligonucleotide probes on a flat, non-porous substrate is well known in the art (see eg. T.P.Theriault: DNA diagnostic systems based on novel Chem-Jet technologies, IBC Conference on Biochip Array Technologies, Washington DC, May 10 1995).

According to a preferred embodiment, the nucleotide compounds are applied using electrostatic attraction. Electrostatic attraction diminishes the risk of splattering.

According to an alternative method of manufacturing a device comprising through-going channels according to the invention, the first binding substance is applied to the through-going channels of a particular area using ink-jet technology. This allows for purification of the first binding substance, and for example in case of an oligonucleotide probe for verification of its sequence, before application to the substrate.

For the reasons mentioned earlier, it is again preferred if the first binding substance is applied using electrostatic attraction.

The present invention also relates to the use of an electrochemically manufactured metal oxide membrane, preferably an aluminium oxide membrane, in the manufacture of any of the above described devices.

According to a preferred embodiment, a temperature difference is adjusted  
5 between different locations on the membrane during performance of the assay to create different hybridisation conditions at different membrane locations.

The use advantageously comprises a nucleic acid hybridisation assay or an immunological assay. In such an assay, a sample which comprises an analyte is brought into contact with a device according to the invention. The  
10 analyte is subsequently allowed to bind to the first binding substance which is attached to the substrate. Such binding is greatly facilitated by allowing the analyte to migrate through the porous substrate. Detection of binding can be performed by adding a second binding substance attached to a label, allowing said second binding substance to bind to the complex of first binding substance  
15 and analyte and determining whether the label is present at the position where the first binding substance was immobilised. Alternatively, the analyte may already have been provided with a label, in which case binding to the first binding substance can be detected directly, without the addition of a second binding substance.

20 The present invention also relates to a kit comprising any of the above mentioned devices which kit additionally comprises a detection means for determining whether binding has occurred between the first binding substance and the analyte. Preferably, such detection means may be a second binding substance provided with a label. Preferably, the label is capable of inducing a  
25 colour reaction and or capable of bio- or chemo- or photoluminescence.

The present invention also relates to a method for the detection of an analyte in a sample comprising the steps of

- a) contacting the sample with any of the above described devices,
- b) allowing binding to take place between the first binding substance and  
30 the analyte,



- c) detecting whether binding has occurred between first binding substance and analyte

In this method the analyte may be a nucleic acid probe, an antibody, an antigen, a receptor, a hapten, and a ligand for a receptor.

- 5 The present invention will now be illustrated by the following examples.

#### Example 1

Simultaneous detection of two different types of HIV-1 amplificate, a Wild Type RNA (WT) and a Calibrator RNA (Qa) using an aluminium oxide membrane in a  
10 flow through cell.

#### **Analytes:**

The WT-RNA and the Qa-RNA fragments represent a part from the GAG region of the HIV-1 genome. These fragments have equal lengths (145nt) and identical  
15 sequences, apart from a 21nt long region in the central part of the fragment. The sequences of the fragments are:

WT-RNA : 5'cccugcuaugucacuuccccuugguucucucaucuggccuggug  
caauaggcccugcaugcacuggaugcacucuaucccauucugcag  
20 cuuccucauugauggucucuuuuuacauuugcauggcugcuugau  
guccccccacu3' (SEQID. NO.1)

Qa-RNA: 5'cccugcuaugucacuuccccuugguucucucaucuggccuggug  
caauaggcccugcaugcgacugucaucaucauacacugucugcag  
25 cuuccucauugauggucucuuuuuacauuugcauggcugcuuga  
ugccccccacu3' (SEQID. NO.2)

The sequence of the WT and Qa specific parts are underlined.

- 30 In this example two buffered solutions were used:

A phosphate buffer at pH 7.4 containing 8g/l NaCl, ("incubation buffer").

A phosphate buffer at pH 7.4 containing 8g/l NaCl and 0.05% Polysorbate (Tween 20), hereinafter denoted "wash buffer".

**Substrate:**

Aluminium oxide membrane, thick 60 $\mu$ m, diameter 24mm. Channels are 0.2 $\mu$ m diameter, density is about 18 channels/ $\mu$ m<sup>2</sup> ("Anodisc 25", Whatman).

The membrane surface is coated with streptavidin by immersing the membrane in the incubation buffer contained 2g/l streptavidin for 60 min. Subsequently, the membranes are washed using the wash buffer and air dried at room temperature.

**10 Immobilisation of first binding substance**

Two oligonucleotide probes, partially complementary to the WT- and QA fragments are applied:

WT-probe: 5'GAATGGGATAGAGTGCATCCAGTG3' (SEQID. NO. 3)

Qa-probe: 5'GACAGTGTAGATAGATGACAGTCG3' (SEQID. NO. 4)

15

both with a biotin molecule coupled to the 5' end.

Spots with a specific diameter are applied using a porous tip (nylon feeder) as found in the common "fineliner" writing pen (Hauser schreibtechnik GmbH, Gosheim Germany). Whereas the feeder tip spots the membrane, its other end is in fluid contact with a reservoir containing the probe solution (incubation buffer, probe concentration 25 $\mu$ mol/L). Transfer of probe solution into the membrane is well controlled by the capillary interaction of membrane and feeder: the probe solution autonomously fills up those channels that are in physical contact with the feeder tip. In this example 2 lines with 3 spots of 0.5mm diameter have been used (3 spots for each probe type). The distance between individual spots was 1 mm. After spotting and an incubation phase of 10 min. at room temperature, unbound probe material is washed away using the wash buffer.

25

In this example, 4 identical substrates were produced in this way.

**Hybridisation**

Next, the membranes are introduced in a flow through cell and brought into contact with the incubation buffer containing the HIV RNA fragments.

30

Four sets of hybridisation conditions have been applied in 4 different experiments:

- 1 volume 25µl containing  $1.5 \cdot 10^{12}$  molecules of QA RNA, no flow
- 2 volume 25µl containing  $1.5 \cdot 10^{12}$  molecules of WT RNA, no flow
- 3 volume 25µl containing  $1.5 \cdot 10^{12}$  molecules of QA RNA, continuous flow
- 5 4 volume 25µl containing  $1.5 \cdot 10^{12}$  molecules of WT RNA, continuous flow

With experiment 1 and 2 there is no transport of the buffer through the membrane.

With experiment 3 and 4, the 25µl RNA solution continuously flows through the membrane in two directions (back and forth) with a velocity of about 25µl/min.

To control this flow, an automated Hamilton dispenser was used.

- 10 With all experiments hybridisation was at room temperature during 10 min.

#### **Washing**

After hybridisation the membranes are washed using 5ml of the wash buffer.

#### **Labelling and detection**

- For detection, a probe that is generic for HIV RNA (SEQID #5) is allowed to
- 15 interact with the membranes. This probe is contained in the incubation buffer (40nmol/L). In each experiment a volume of 75 µl is used, without flow. The probes are labelled with the horseradish peroxidase (HRP) enzyme in a 1:1 ratio, using maleimide containing heterobifunctional cross-linkers (Hashida, S., et al. (1984) J. Applied Biochem. 56, 56-63). Prior to the HRP coupling the probes
  - 20 were thiolated (Carlsson, J., et al. (1978) Biochem. J. 173, 723-737).

After washing with 10ml wash buffer, a solution containing 3,3',5,5'-tetramethylbenzidine hydrogenperoxide, TMB (Organon Teknika, art: 78510), is brought into contact with the membranes (no flow).

#### **Result:**

- 25 Interpretation of the results was with the unaided eye. In experiment 3 and 4, blue spots appear almost immediately at a location where a specific reaction is expected (spots containing WT probes turn blue using WT-RNA and spots containing Qa probes turn blue using Qa-RNA). With the spots containing probes that are not complementary to the RNA in the buffer no colouring was observed,
- 30 although the area on the membrane in between the spots shows a slight bluish colour after several minutes, probably due to insufficient washing or some non

specific binding. In experiment 1 and 2 a similar result is obtained, however, in these cases it takes about a minute before blue spots become visible.

In addition to the visual evaluation of the spots during the TMB reaction, the spots  
5 on the membranes in experiments 3 and 4 were evaluated using an imaging densitometer (Biorad GS700). To this end the membranes were removed from the flow-through cells (Table 1)

Table 1 Density of spots measured with densitometer

RNA analyte	spot with WT- probes [OD units]	spot with Qa- probes [OD units]	background area [OD units]
WT-RNA	38	20	20
Qa-RNA	25	35	25

10

#### Example 2

Oligonucleotide probes were covalently coupled to the Anopore membranes using 3-aminopropyl triethoxysilane (APS) as a linker between the alumina and the oligo. For the experiments Anodics 25 membranes with a diameter of 25 mm and  
15 a total surface area of 0.3 m<sup>2</sup> were used.

The membranes were activated by immersion in a nitric acid solution (0.4 mol/l) during 1 hour. After rinsing with water the membranes were dried and immersed in a 0.25% (v/v) solution of APS in water for 2 hours. Excess APS was removed by rinsing with water. After drying at 120°C at reduced pressure the membranes  
20 were stored. Amino group concentration due to the coupling of the APS molecules was typical 2-3  $\mu\text{mol}/\text{m}^2$ .

Before coupling, the amino group terminated oligo nucleotides were activated by reaction with disuccinimidyl suberate (DSS, see eg. PIERCE BV, Immunotechnology Catalog & Handbook, 1990). The resulting succinimidyl group  
25 at the end of the oligo was used for coupling to the APS activated membrane. Labelling with <sup>32</sup>P was used for quantification of the results. Coupling with 500  $\mu\text{l}$

oligo solution on an Anodisc membrane during 60 minutes resulted in a coupling yield of  $1 \cdot 10^{-10}$  mol/m<sup>2</sup> oligo nucleotide.

### **Example 3**

- 5 Definition of an array pattern on an Al<sub>2</sub>O<sub>3</sub> membrane using an ink-jet device.
- Using standard ink-jet technology small droplets having a diameter of 20-80 µm can be generated and positioned on a substrate at high throughput rates at µm resolution. Using a commercially available desk-jet (HP 660C) in combination with the Al<sub>2</sub>O<sub>3</sub> membranes arrays of a very high resolution have been obtained.
- 10 Visual inspection with a microscope (magnification: 400x) shows perfectly round spots of approx. 60µm diameter having very sharp margins. No signs of splattering, as is commonly observed when using non-porous surfaces was observed. We attribute the high array resolution to the high porosity of the material in combination with the hydrophilic character of the through-going
- 15 channels.

### **Example 4**

Performing a sandwich immuno assay.

- 20 Detection of human chorionic gonadotrophin (hCG) with an enzyme immuno assay using an aluminium oxide membrane as solid phase.

#### **Coating of the membrane**

- Small areas of aluminium oxide membranes (round with a diameter of 20 mm)
- 25 were coated with a buffered solution (0.0127 mol/l phosphate and 0.140 mol/l NaCl at pH 7.4) containing 1 µg/ml monoclonal mouse antibody (OT-hCG-4B) directed against hCG. The solution was applied by pipetting 10 µl droplets onto the membrane or by contact spotting using a polyester feeder (Hauser). After incubation at 37°C for 30 minutes the membranes are ready for use.

30

#### **Incubation**

The positive samples were a mixture of 50 ul hCG with a concentration of 2000 IU/l and 50 ul mouse anti-hCG (OT-hCG-3A) conjugated with hors radish peroxidase (HRP) (1 ug/ml). This mixture was pre-incubated for 15 minutes. In the case of the negative control 50 ul buffer was mixed with 50 ul conjugate solution.

Next the mixture (100 ul) was pipetted onto the membranes and incubated for 15 minutes at room temperature.

#### **Washing and detection**

The membranes were extensively rinsed with a washing buffer (0.131 mol/l NaCl, 0.0127 mol/l phosphate and 0.5 ml/l Polysorbate 20) on a funnel. Finally the membranes were placed in a beaker containing a substrate for HRP based on 3,3',5,5'- tetramethylbenzidine and hydrogen peroxide (Organon Teknika). During 30 minutes incubation the results were observed visually and with a camera.

#### **Results**

Clear blue spots became visible within a few minutes where the membranes were coated with OT-hCG-4B in the case of the positive samples. On the other parts of the membrane and with the negative control only a faint blue background colour could be observed after relative long incubation.

CLAIMS

1. A device for performing an assay, which device comprises a substrate having oriented through-going channels, said channels opening out on a surface for sample application, the channels in at least one area of the surface for sample application being provided with a first binding substance capable of binding to an analyte, wherein the substrate is an electrochemically manufactured metal oxide membrane.
2. The device according to claim 1, wherein the first binding substance is chosen from the group consisting of a nucleic acid probe, an antibody, an antigen, a receptor, a hapten and a ligand for a receptor.
3. The device according to claim 1 or 2, wherein the first binding substance is covalently bound to the substrate.
4. The device according to any of the preceding claims, wherein the metal oxide membrane is comprised of aluminium oxide.
5. A method of manufacturing a device according to any of the preceding claims, wherein the first binding substance is synthesised in situ.
6. The method according to claim 5, wherein a compound for synthesising the first binding substance is applied to a particular area using ink-jet technology.
7. The method according to claim 6, wherein the compound is applied using electrostatic attraction.

8. A method of manufacturing a device according to any of the claims 1 - 4, wherein the first binding substance is applied to a particular area using ink-jet technology.
- 5 9. The method according to claim 8, wherein the first binding substance is applied using electrostatic attraction.
- 10 10. Use of an electrochemically manufactured metal oxide membrane in the manufacture of a device according to any of the claims 1 - 4. performing a probe-based assay.
11. A kit comprising a device according to any of the claims 1 - 4, said kit additionally comprising a detection means for determining whether binding has occurred between the first binding substance and the analyte.
- 15 12. Kit according to claim 11 wherein the detection means comprises a second binding substance provided with a label.
- 13 13 Kit according to claim 12 wherein the label is capable of inducing a colour reaction and/or capable of bio- or chemo- or photoluminescence.
- 20 14. A method for the detection of an analyte in a sample comprising the steps of
- a) contacting the sample with a device according to any of the claims 1-4,
- b) allowing binding to take place between the first binding substance and
- 25 the analyte
- c) detecting whether binding has occurred between first binding substance and analyte.
- 15 15 The method of claim 14 wherein the analyte comprises nucleic acid.



16. The method of claim 15 wherein the nucleic acid is derivable from human immunodeficiency virus.

## SEQUENCE LISTING

## (1) GENERAL INFORMATION:

5

## (i) APPLICANT:

- (A) NAME: Akzo Nobel N.V.  
(B) STREET: Velperweg 76  
(C) CITY: Arnhem  
(E) COUNTRY: The Netherlands  
(F) POSTAL CODE (ZIP): 6824 BM  
(G) TELEPHONE: 0412 666380  
(H) TELEFAX: 0412 650592

15

- (ii) TITLE OF INVENTION: A device for performing an assay, a method  
for manufacturing said device, and use of a membrane in  
the manufacture of said device

- (iii) NUMBER OF SEQUENCES: 5

20

## (iv) COMPUTER READABLE FORM:

- (A) MEDIUM TYPE: Floppy disk  
(B) COMPUTER: IBM PC compatible  
(C) OPERATING SYSTEM: PC-DOS/MS-DOS  
(D) SOFTWARE: PatentIn Release #1.0, Version #1.30 (EPO)

25

## (2) INFORMATION FOR SEQ ID NO: 1:

30

## (i) SEQUENCE CHARACTERISTICS:

- (A) LENGTH: 145 base pairs  
(B) TYPE: nucleic acid  
(C) STRANDEDNESS: single  
(D) TOPOLOGY: linear

35

- (ii) MOLECULE TYPE: RNA (genomic)

40

## (xi) SEQUENCE DESCRIPTION: SEQ ID NO: 1:

CCCUGCUAUG UCACUUGCCC UUGGUUCUCU CAUCUGGCCU GGUGCAAUAG GCCCUGCAUG 60

45 CACUGGAUGC ACUCUAUCCC AUUCUGCAGC UUCCUCAUUG AUGGUCUCUU UUAACAUUUG 120

CAUGGCUGCU UGAUGUCCCC CCACU 145

2/3

## (2) INFORMATION FOR SEQ ID NO: 2:

- 5 (i) SEQUENCE CHARACTERISTICS:  
(A) LENGTH: 145 base pairs  
(B) TYPE: nucleic acid  
(C) STRANDEDNESS: single  
(D) TOPOLOGY: linear
- 10 (ii) MOLECULE TYPE: RNA (genomic)

## 15 (xi) SEQUENCE DESCRIPTION: SEQ ID NO: 2:

CCCUGCUAUG UCACUUGCCC UUGGUUCUCU CAUCUGGCCU GGUGCAAUAG GCCUGCAUG 60  
CGACUGUCAU CUAUCUACAC UGUCUGCAGC UUCCUCAUUG AUGGUCUCUU UUAACAUUUG 120  
20 CAUGGCUGCU UGAUGUCCCC CCACU 145

## (2) INFORMATION FOR SEQ ID NO: 3:

- 25 (i) SEQUENCE CHARACTERISTICS:  
(A) LENGTH: 24 base pairs  
(B) TYPE: nucleic acid  
(C) STRANDEDNESS: single  
(D) TOPOLOGY: linear
- 30 (ii) MOLECULE TYPE: DNA (genomic)

35

## (xi) SEQUENCE DESCRIPTION: SEQ ID NO: 3:

GAATGGGATA GAGTGCATCC AGTG

## 40 (2) INFORMATION FOR SEQ ID NO: 4:

- (i) SEQUENCE CHARACTERISTICS:  
(A) LENGTH: 24 base pairs  
(B) TYPE: nucleic acid  
45 (C) STRANDEDNESS: single  
(D) TOPOLOGY: linear

(ii) MOLECULE TYPE: DNA (genomic)

5

(xi) SEQUENCE DESCRIPTION: SEQ ID NO: 4:

GACAGTGTAG ATAGATGACA GTCG

10

(2) INFORMATION FOR SEQ ID NO: 5:

(i) SEQUENCE CHARACTERISTICS:

(A) LENGTH: 25 base pairs

(B) TYPE: nucleic acid

15

(C) STRANDEDNESS: single

(D) TOPOLOGY: linear

(ii) MOLECULE TYPE: DNA (genomic)

20

(xi) SEQUENCE DESCRIPTION: SEQ ID NO: 5:

25

TGTTAAAAGA GACCATCAAT GAGGA

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/04938

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 B01L3/00 C12Q1/68

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01L C12Q

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 11755 A (HOUSTON ADVANCED RES CENTER ;BEATTIE KENNETH L (US)) 4 May 1995 cited in the application see the whole document ---	1-16
A	RIGBY WR ET AL: "An anodizing process for the production of inorganic microfiltration membranes" TRANSACTION OF THE INSTITUTE OF METAL FINISHING, vol. 68, no. 3, 1990, pages 95-98, XP000160294 cited in the application see page 95 - page 98 ---	1-4
A	GB 1 432 713 A (CORNING GLASS WORKS) 22 April 1976 see the whole document ---	1-4
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

30 November 1998

Date of mailing of the international search report

08/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651.epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Runser, C

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP 98/04938

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 652 761 A (WEETALL HOWARD H) 28 March 1972 see the whole document ---	1-4
A	FADDA M B ET AL: "COVALENT COUPLING OF CONCAVALIN A TO COMMERCIAL ALUMINA" BIOTECHNOLOGY AN APPLIED BIOCHEMISTRY, vol. 16, 1992, pages 221-227, XP002050223 cited in the application see page 221 - page 222 -----	1-4

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/04938

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9511755 A	04-05-1995	AU 1043595 A CA 2174140 A EP 0725682 A JP 9504864 T	22-05-1995 04-05-1995 14-08-1996 13-05-1997
GB 1432713 A	22-04-1976	BE 817434 A DE 2429196 A FR 2236872 A JP 50043090 A	09-01-1975 06-02-1975 07-02-1975 18-04-1975
US 3652761 A	28-03-1972	AT 309675 B BE 755775 A CA 955523 A DE 2042976 A FR 2060904 A GB 1288328 A NL 7013059 A	15-07-1973 04-03-1971 01-10-1974 11-03-1971 18-06-1971 06-09-1972 08-03-1971